

New Zealand Perlite

除滓材・パーライト



SiO₂	74.0%	Micron /Mesh	British	USA	05F	101	105	205	310
Al₂O₃	14.0%	3.350mm	5	6					0-10%
Fe₂O₃	1.0%	2.800mm	6	7					10-25%
CaO	1.3%	2.000mm	8	10				0-20%	40-60%
MgO	0.3%	1.180mm	14	16			0-5%		
K₂O	4.0%	1.000mm	6	18			5-15%	60-75%	95-100%
Na₂O	3.0%	0.850mm	18	20		0-5%			
TiO₂	0.1%	0.710mm	22	25			45-70%		
Ig.Loss	3.0%	0.600mm	25	30	0-15%				
Specific Gravity	1.0kg/l	0.500mm	35	35		65-70%	95-100%	90-100%	
		0.425mm	36	40					
		0.300mm	52	50	90-100%	95-100%			
		Recommended Application Temp(°C)			1,350-1,390	1,390-1,430	1,430-1,470	1,470-1,510	1,510-1,550